



FLX-DRY CEMENT D/5

DRY CEMENT DISCHARGE HOSE-5 bar WP.

Application

Transfer of cement, gravel, sand and general abrasive dry materials.

Tube

Black, smooth, static-dissipating NR/SBR rubber compound.

Reinforcement

High strength synthetic plies.

Cover

Wrapped impression, abrasion and weather resistant NR/SBR rubber compound.

Temp. Range

-40°C to +85°C ; -40°F to 185°F



ID



OD



WP



BP



W



L

inch	mm	mm	BAR	PSI	BAR	PSI	gr/mt	mt
1/8" TUBE THICKNESS								
4"	101.6	113	5	75	15	225	2380	61
5"	127	139	5	75	15	225	2900	61
3/16" TUBE THICKNESS								
4"	101.6	118	5	75	15	225	3350	61
5"	127	144	5	75	15	225	4200	61
1/4" TUBE THICKNESS								
4"	101.6	121	5	75	15	225	3839	61
5"	127	147	5	75	15	225	4658	61

Abrasion loss value of the tube $\leq 50 \text{ mm}^3$ (according to DIN ISO 4649:2006)